



BIOSMOOTHER

RAS.BIO



PRODUCT DESCRIPTION

Naturalcalk Biorasante is made of lime putty seasoned according to UNI EN 459-1 standard and selected fine inert materials, without cements and chemical additives. Naturalcalk Biorasante is excellent to use to give the facades an ideal support for subsequent lime finishes. To ensure fixing to the support, we recommend pre-consolidation with Naturalcalk antibacterial fixative.

FIELDS OF USE AND PRODUCT APPLICATION

Apply the first coat of Naturalcalk Biorasante after cleaning the support from dust or sawing due to cutting, down the plaster holder mesh, and wait 24 hours to apply the second coat to prepare the final finish.

Naturalcalk Biorasante is applied with a steel spatula; when the setting begins, it should be finished with a sponge or lamato trowel to get a finished painting appearance. For subsequent marmorino finishes or other applications, just finish with a steel trowel.

Protect the application from the rain for about 48 hours and do not apply at air temperatures below 5°C or higher than 25°C and on walls overheated by the sun. In hot and breezy periods, it is necessary to moisten the walls.

Before use, shake mechanically until the mixture is homogeneous.

Why should you choose Naturalcalk Biorasante?

- It is ready to use.
- It anchors perfectly (detachment load 15 KGF/square centimeter).
- Resists to alkaline aggression.
- It resists to bacterial aggression of molds and mosses.
- It offers effective resistance to abrasion.
- Salt spray resistant (ASTM-B117 standard at 550 hours).
- It is not flammable.
- Wet specific weight 1,4 kg/L.
- Vapor permeability M.65; SD.O, 04M.
- pH 12.

WARNINGS

The exclusive use of the products of the Natural Calk line is absolutely strict in every processing phase of the Tillica Pasta system in order to maintain the characteristics of the system and guarantee the result.

The company takes on solely responsibility for the product up to the departure of the material from the deposit/supplier Arte e Mestieri SRL, while the application, use, and processing are the exclusive responsibility of the customer or the applicator. The company reserves the right to modify the composition, keeping the characteristics naturally unchanged.

